General Solid Carbide Milling Guide *Fractional*

Туре	Rc	MILLING SFM (Vc)					CHIPLOAD PER FLUTE (Fz)				
	Hardness	2 flute stub / std.	2 flute extra length	3 & 4 flute stub / std.	3 & 4 flute extra length	Diamond Coated	1/32" - 1/8"	1/8" - 1/4"	1/4" - 1/2"	1/2" - 1"	1" - 1-1/4"
Powdered Metal, Stellite, Hs-21, Haynes 25/188, X-40, L-605	< 35 > 35	-	-	175 - 225 125 - 175	3ALT BASE 150 - 200 100 - 150	-	.0005"0010" .0003"0005"	.0008"0020" .0005"0015"	.0010"0030" .0010"0020"	.0020"0040" .0010"0030"	.0030"0050" .0020"0040"
Invar, Kovar, Inconel-625/718, Waspalloy, Rene, Hastalloy, A286	< 35 > 35	-	-	125 - 175 70 - 115	KEL BASE 100-150 70-100	-	.0005"0010" .0003"0005"	.0008"0020" .0005"0015"	.0010"0030" .0010"0020"	.0020"0040" .0010"0030"	.0030"0050" .0020"0040"
Incoloy 800-802, Multimet N-155, Timkin 16-25-6, Carpenter 22-b3	< 35 > 35	-	-	IRC 175 - 225 125 - 175	DN BASE 150-200 100-150	-	.0005"0010" .0003"0005"	.0008"0020" .0005"0015"	.0010"0030" .0010"0020"	.0020"0040" .0010"0030"	.0030"0050" .0020"0040"
Monel - 65% Nickel		175 - 300	125 - 175	175 - 300	MONE 125 - 175	=L -	.0007"0015"	.0010"0025"	.0015"0040"	.0030"0050"	.0040"0060"
TITANIUM ALLOYS											
Commercially Pure, 6AI-4V, Astm 1/2/3, 6AI-25N-4Zr-2Mo-Si		200 - 300	125 - 250	200 - 300	125 - 250	-	.0007"0015"	.0010"0025"	.0015"0040"	.0030"0050"	.0040"0060"
5553 / Beta Titanium		-	-	125 - 225	100-200	-	.0005"0010"	.0008"0020"	.0010"0030"	.0020"0040"	.0030"0050"
12/0 15/5 17 4 117	< 35	-	-	150 - 250	AINLESS 100-150	-	.0005"0010"	.0008"0020"	.0010"0030"	.0020"0040"	.0030"0050"
13/8, 15/5, 17-4, pH Types	> 35 < 35	-	-	125 - 175 200 - 250	80 - 150 125 - 175	-	.0003"0005" .0005"0010"	.0005"0015" .0008"0020"	.0010"0020" .0010"0030"	.0010"0030" .0020"0040"	.0020"0040" .0030"0050"
	> 35 < 35	-	-	150 - 200 90 - 125	100 - 150 80 - 120	-	.0003"0005" .0005"0008"	.0005"0015" .0008"0015"	.0010"0020" .0010"0020"	.0010"0030" .0020"0040"	.0020"0040" .0030"0050"
304L, 316L, Nitronic 50, Inox	> 35	-	-	75 - 110	60 - 90	-	.0003"0005"	.0005"0010"	.0010"0015"	.0010"0030"	.0020"0040"
400 Series	< 35 > 35	-	-	150 - 250 125 - 175	100 - 150 80 - 150	-	.0005"0010" .0003"0005"	.0008"0020" .0005"0015"	.0010"0030" .0010"0020"	.0020"0040" .0010"0030"	.0030"0050" .0020"0040"
				HIGH ST	RENGTH	TOOL ST	EELS				
4140, 4340, 6150, 5210, A2, D2, P20, H11, H13, S2, O1	< 30	-	-	150 - 225	125 - 175	-	.0005"0010"	.0008"0020"	.0010"0030"	.0020"0040"	.0030"0050"
	30 - 38	-	-	90 - 125	80 - 120	-	.0003"0005"	.0005"0015"	.0010"0020"	.0010"0030"	.0020"0040"
	> 38	-	-	60 - 90	50 - 80	-	.0002"0004"	.0003"0007"	.0008"0015"	.0010"0025"	.0015"0035"
	< 35		-	175 - 250	И ALLOY ⁻ 150 - 200		EELS .0007"0015"	.0010"0025"	.0015"0040"	.0030"0050"	.0040"0060"
200, 250, 300, 8620	> 35	-	-	100 - 175	100 - 150	-	.0005"0010"	.0008"0020"	.0010"0030"	.0020"0040"	.0030"0050"
126 121 14					ARBON S	TEELS	00078 00158	0010	00151 00401	00001 00501	00401 00501
A36, 12L14, 1000's, 1100's, 1300's	< 35 > 35	-	-	175 - 250 100 - 175	150 - 200 100 - 150 CAST MAT	ERIAL	.0007"0015" .0005"0010"	.0010"0025" .0008"0020"	.0015"0040" .0010"0030"	.0030"0050" .0020"0040"	.0040"0060" .0030"0050"
Steel		225 - 325	175 - 250	250 - 350	175 - 250	-	.0010"0020"	.0015"0040"	.0020"0060"	.0030"0100"	.0050"0100"
Ductile Iron		200 - 300	125 - 200	200 - 300	125 - 200	-	.0005"0015"	.0010"0030"	.0015"0040"	.0020"0060"	.0030"0080"
Gray Iron		225 - 325	175 - 250	250 - 350	175 - 250	-	.0010"0020"	.0015"0040"	.0020"0060"	.0030"0100"	.0050"0100"
Aluminum		250 - 350	250 - 350	250 - 350	250 - 350 ALUMIN	-	.0010"0020"	.0015"0040"	.0020"0060"	.0030"0100"	.0050"0100"
Aircraft Grade (6061, 7075)	Standard Speed High	300 - 500	300 - 500	300 - 500	300 - 500	-	.0010"0020" D ALUMINUM C	.0015"0040" "HART - PAGE 20	.0020"0060"	.0030"0100"	.0050"0150"
	Speed				MAGNES				-)		
		300 - 500	300 - 500	300 - 500	300 - 500	-	.0010"0020"	.0015"0040"	.0020"0060"	.0030"0100"	.0050"0100"
	1				COPPI	ER					
Copper Alloys		300 - 400	250 - 350	300 - 450	250 - 350	-	.0007"0015"	.0010"0025"	.0015"0035"	.0020"0080"	.0040"0100"
Brass, Aluminum/Bronze,		200 400	200 200		BRASS, BR	ONZE	0007" 0015"	.0010"0025"	.0015"0035"	0020" 0000"	.0040"0100"
Low Silicon Bronze		300 - 400	200 - 300	275 - 375	200 - 300	-	.0007"0015"	.00100025"	.00150035"	.0020"0080"	.00400100"
					1POSITE N						
Glass Epoxy, Fiberglass, Plastics		200 - 400	200 - 400	200 - 400	200 - 400	200 - 500	.0010"0020"	.0015"0040"	.0020"0060"	.0030"0100"	.0050"0100"
Graphite, G10		(SEE	GRAPHITE CI	HART - PAGI	E 285)	300 - 1000	.0010"0020"	.0015"0040"	.0020"0060"	.0030"0100"	.0050"0100"

When plunging into a solid, drop feed by approximately 50%. 20% of diameter for basic engagement parameters.

NOTE - ABOVE ARE STARTING PARAMETERS ONLY. HIGHER RESULTS MAY BE ACHIEVED WITH OPTIMUM CONDITIONS.

TECHNICAL



